


# TIMBEREX

WOOD FINISHING OIL



## TIMBEREX® HEAVY DUTY UV PLUS

### Hard wearing oil for commercial and industrial use

- Seals and protects wood from within
- For high traffic areas as airports, museums, conference centres and more
- UV-blockers prevent discoloration
- Protects the wood against liquids and stains
- Protects without losing the 'natural wood look'

# TIMBEREX® HEAVY DUTY UV PLUS

## BESKRIVELSE

Timberex® Heavy Duty UV PLUS uses natural, fast drying oils and resins which penetrate deeply into the wood. Timberex® Heavy Duty UV PLUS has a high coverage, a pleasant smell, very good water resistance and UV resistance and is fast curing. EN 71-3 certified (Toy Safe).

## ANBEFALT BRUK

For high traffic areas as airports, museums, conference centres and more.

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Overmalbar: 20 - 30 minutes  
Herdetid: 7 days

## TEORETISK FORBRUK

12 - 15 m<sup>2</sup> per litre

## PRAKTISK FORBRUK

Coverage on end-grain wood will be greatly reduced. It is recommended that on 'end grain' wood, beech, cherry and other extremely porous woods, a extra coat of oils is applied to reduce excessive absorption.

## KLARGJØRING AV OVERFLATE

Punch down any nail heads, fill any small holes or imperfections with proprietary coloured timber filler (plastic wood) and leave to cure. The wood should not have excessive gaps through which the product could seep and affect the bond of any adhesive layer or rooms below. Floors should be free from any barrier to penetration. Floors should be free from any barrier to penetration. Sand at least twice starting with coarse sandpaper, and use 120 grade maximum sandpaper for the final preparatory sanding. Clean the surface by vacuuming and damp wipe the entire floor and allow to dry.

## BRUKSANVISNING

It is advisable to test a small area first.

1. Apply the first coat of Timberex® Heavy Duty UV Plus using a brush, pad or roller. Accidental splashes on surrounding surfaces must be removed at once.
2. Apply a second coat after 20-30 minutes. Apply coats until the wood will not absorb any more oil. The oil must not dry between coats.
3. After another 20-30 minutes, thoroughly buff the wet surface using a buffer and medium grade nylon pad at approximately 150 rpm. Can be done manually as well.
4. Remove ALL unabsorbed Timberex® Heavy Duty UV Plus immediately with cloths, leaving a matt finish at this stage. Place all oil-impregnated cloths etc. into a bucket filled with water. See 'SAFETY' for further information.
5. When the surface has dried after 5-9 hours, it is important to thoroughly buff with a medium grade nylon pad to close the surface, provide a satin sheen and to remove any minor 'bleed-back'.

## RENGJØRING AV UTSTYR/SPILL

Mild solvent, white spirit etc.

## MERKNADER

EQUIPMENT: Drum sander, sandpaper including 120 grade for final preparatory sanding, buffing machine (150-300 rpm), wide brush or platform pad, Red grade (3M) nylon buffing pads, absorbent cloths and water bucket.

MAINTENANCE AND CLEANING: Floors which have been oiled for the first time should be treated with Timberex® Satin Oil maintenance products after 6-12 months and thereafter once a year or when needed. Avoid alkaline soaps. Use Timberex® Bio-C Cleaner for regular cleaning.

CURING: The surface will normally be sufficiently dry to walk on after 24 hours. Dry vacuum only during the first 7 days and remove liquid spillages immediately. The surface will gradually increase in water resistance. Any initial light water marking is easily removed by soft nylon pad in conjunction with Timberex® Maintenance products and cleaners.

## HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 24/03/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)