

TIMBEREX

WOOD FINISHING OIL



TIMBEREX® SATIN OIL

Maintenance oil for oil treated surfaces

- Labour-efficient, easy and rapid maintenance
- Surface dry after 6-10 hours
- Re-sanding normally not necessary
- One layer is sufficient

TIMBEREX® SATIN OIL

OPIS

TIMBEREX® Satin Oil is used for periodic maintenance of floors treated with natural drying oils. EN 71-3 certified (Toy Safe).

ZAŁECANE UŻYCIE

TIMBEREX® Satin Oil is used for periodic maintenance of floors treated with natural drying oils.

DANE TECHNICZNE

Gęstość: 0.82
Stopień połysku: Satyna

CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Do przemaalowania: 20 - 45 minutes
Pełne utwardzenie: 7 days

ŻUŻYCIE TEORETYCZNE

15 - 20 m² per litre

ŻUŻYCIE PRAKTYCZNE

Can vary depending on wood-specie, condition and preparation.

PRZYGOTOWANIE POWIERZCHNI

Clean the floor using TIMBEREX® Bio-C Cleaner and allow to dry.

WSKAZÓWKI DOTYCZĄCE UŻYCIA

It is advisable to test a small area first. For maintenance with TIMBEREX® Satin Oil **layer** is normally sufficient.

1. Apply TIMBEREX® Satin Oil using a brush, pad or roller. Accidental splashes on surrounding surfaces must be removed at once.
2. If necessary, apply a second coat after 20 - 45 minutes. Apply coats until the wood will not absorb any more oil. The oil must not dry between coats.
3. After another 20-45 minutes, thoroughly buff the wet surface using a buffer and medium grade nylon pad at approximately 150 rpm. Can be done manually as well.
4. Remove ALL unabsorbed TIMBEREX® Satin Oil immediately with cloths, leaving a matt finish at this stage. Place all oil-impregnated cloths etc. into a bucket filled with water. See 'SAFETY' for further information.
5. When the surface has dried after 6-10 hours, it is important to thoroughly buff with a medium grade nylon pad to close the surface, provide a satin sheen and to remove any minor 'bleed-back'.

CZYSZCZENIE NARZĘDZI / ZABRUDZEŃ

Mild solvent, white spirit etc.

UWAGI

EQUIPMENT: Buffing machine (150-300 rpm), squeegee or platform pad Red (3M) nylon buffing pads, absorbent cloths and water bucket.

MAINTENANCE AND CLEANING: Floors which have been oiled for the first time should be treated with TIMBEREX® Satin Oil maintenance products after 6-12 months and thereafter once a year or when needed. Avoid alkaline soaps. Use TIMBEREX® Bio-C Cleaner for regular cleaning.

CURING: The surface will normally be sufficiently dry to walk on after 24 hours. Dry vacuum only during the first 7 days and remove liquid spillages immediately. The surface will gradually increase in water resistance. Any initial light water marking is easily removed by soft nylon pad in conjunction with TIMBEREX® Maintenance products and cleaners.

INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO w gotowej

mieszance:

Uwagi dotyczące

bezpieczeństwa:

691g/L

When sanding and sealing floors protective clothing should be worn including a face mask for dust filtration.

All product labels provide general safety information. Material safety data sheets are available on www.timberex.com. Food products must be removed from the area during application and cure.

Applicators, cloths etc impregnated with the product should be put in a bucket of water and placed outside the building to avoid the possibility of spontaneous combustion. The contents should be disposed of according to local regulations.

OKRES TRWAŁOŚCI PRODUKTU

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Data wydania: 24/03/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu