

TIMBEREX

WOOD FINISHING OIL



TIMBEREX® THIXO

Transparent thixotropic wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film forming
- Enhances the wood structure

TIMBEREX® THIXO

ОПИСАНИЕ

Slight thixotropic solvent based wood stain based on special urethane modified linseed oil alkyd resins. TIMBEREX® Thixo is an easy to apply thixotropic stain with great protective and cosmetic qualities with a slightly thicker texture than other wood-stains. This allows for a thicker coating of the product to be applied for better long-term protection and makes it more convenient to use, especially for overhead work. Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance – micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

ПРЕПОРЪЧАНА УПОТРЕБА

Protective and decorative impregnation of interior and exterior woodwork. Remark: colourless TIMBEREX Thixo is only suitable for internal use.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit or similar.

Old stripped paint: rub down up to the bare non-impregnated wood and remove all dust before application.

Maintenance: clean substrate with white spirit and apply 2 or 3 thin coats of TIMBEREX Thixo.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	0.86 - 0.89
Гланцово ниво:	semi_mat
Съдържание на твърди частици в тегло:	37 - 40%
Съдържание на твърди вещества в обема:	30 - 33%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	3 hours
Сух за употреба:	3 hours
Готов за повторно нанасяне:	24 hours

МОКЪР СЛОЙ

100 micron (cons.: 10 m²/l)

СУХ СЛОЙ

32 micron (cons.: 10 m²/l)

РАЗХОДНА НОРМА

10 m²/l

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

НАЧИН НА УПОТРЕБА

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

УСЛОВИЯ ЗА НАНАСЯНЕ

Apply in a dry and well-ventilated area.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

By preference, apply undiluted.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

By preference, apply undiluted.

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

By preference, apply undiluted.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

White spirit or similar

ЗАБЕЛЕЖКИ

Incorrect use of TIMBEREX Thixo means that it can still be fully or partly removed with White Spirit within the first few days after application.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	max. 550 g/l
Готов за употреба ЛОС (VOC Ready mix):	max. 550 g/l
Категория ЛОС:	IIA/f
Ограничение за ЛОС:	700g/l
Забележки относно безопасността:	Consult Safety Data Sheet and Safety. Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Дата на издаване: 24/03/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu