

# TIMBEREX

WOOD FINISHING OIL



## TIMBEREX® THIXO

### Transparent thixotropic wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film forming
- Enhances the wood structure

# TIMBEREX® THIXO

## DESCRIPTION

Slight thixotropic solvent based wood stain based on special urethane modified linseed oil alkyd resins. TIMBEREX® Thixo is an easy to apply thixotropic stain with great protective and cosmetic qualities with a slightly thicker texture than other wood-stains. This allows for a thicker coating of the product to be applied for better long-term protection and makes it more convenient to use, especially for overhead work. Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance – micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

## DOPORUČENÉ POUŽITÍ

Protective and decorative impregnation of interior and exterior woodwork. Remark: colourless TIMBEREX Thixo is only suitable for internal use.

## DOPORUČENÝ SYSTÉM

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit or similar.

Old stripped paint: rub down up to the bare non-impregnated wood and remove all dust before application.

Maintenance: clean substrate with white spirit and apply 2 or 3 thin coats of TIMBEREX Thixo.

## TECHNICAL\_DATA

Hustota (g/cm <sup>3</sup> ):	0.86 - 0.89
Úroveň lesku:	Semi-Matt
Obsah pevných látek v hmotnosti:	37 - 40%
Obsah pevných látek v objemu:	30 - 33%

## DRY TIMES BY 20° C/RH 50%

Dotykem suché:	3 hours
Suché na manipulaci:	3 hours
Suchý nátěr:	24 hours

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 micron (cons.: 10 m<sup>2</sup>/l)

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

32 micron (cons.: 10 m<sup>2</sup>/l)

## TEORETICKÁ SPOTŘEBA

10 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Apply in a dry and well-ventilated area.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

By preference, apply undiluted.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

By preference, apply undiluted.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

By preference, apply undiluted.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit or similar

## POZNÁMKY

Incorrect use of TIMBEREX Thixo means that it can still be fully or partly removed with White Spirit within the first few days after application.

## SAFETY DATA

Úroveň těkavých organických

látek: max. 550 g/l

VOC readymix: max. 550 g/l

Kategorie VOC: IIA/f

Limitní hodnota VOC: 700g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety. Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last\_updated: 24/03/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu