

TIMBEREX

WOOD FINISHING OIL



TIMBEREX® THIXO

Transparent thixotropic wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film forming
- Enhances the wood structure

TIMBEREX® THIXO

BESCHREIBUNG

Slight thixotropic solvent based wood stain based on special urethane modified linseed oil alkyd resins. TIMBEREX® Thixo is an easy to apply thixotropic stain with great protective and cosmetic qualities with a slightly thicker texture than other wood-stains. This allows for a thicker coating of the product to be applied for better long-term protection and makes it more convenient to use, especially for overhead work. Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance – micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

EMPFOHLENE VERWENDUNG

Protective and decorative impregnation of interior and exterior woodwork. Remark: colourless TIMBEREX Thixo is only suitable for internal use.

EMPFOHLENES SYSTEM

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit or similar.

Old stripped paint: rub down up to the bare non-impregnated wood and remove all dust before application.

Maintenance: clean substrate with white spirit and apply 2 or 3 thin coats of TIMBEREX Thixo.

TECHNISCHE DATEN

Dichte (g/cm ³):	0.86 - 0.89
Glanzgrad:	["Semi-Matt"]
Feststoffgehalt in Gewicht:	37 - 40%
Feststoffgehalt in Volume:	30 - 33%

TROCKENZEITEN BEI 20°C/RF 50%

Klebfrei:	3 hours
Griffest:	3 hours
Überstreichbar:	24 hours

EMPFOHLENE NASSE SCHICHTDICKE

100 micron (cons.: 10 m²/l)

EMPFOHLENE TROCKENSCHICHTDICKE

32 micron (cons.: 10 m²/l)

THEORETISCHE ERGIEBIGKEIT

10 m²/l

PRAKTISCHE ERGIEBIGKEIT

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

HINWEISE ZUR VERARBEITUNG

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANWENDUNGSBEDINGUNGEN

Apply in a dry and well-ventilated area.

VERDÜNNUNG & ANWENDUNG: PINSEL

By preference, apply undiluted.

VERDÜNNUNG & ANWENDUNG: ROLLER

By preference, apply undiluted.

VERDÜNNUNG & ANWENDUNG: AIRLESS SPRITZEN

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars

VERDÜNNUNG & ANWENDUNG: DRUCKLUFTSPRITZ

By preference, apply undiluted.

REINIGUNG DER ARBEITSGERÄTE / SPRITZER

White spirit or similar

BEMERKUNGEN

Incorrect use of TIMBEREX Thixo means that it can still be fully or partly removed with White Spirit within the first few days after application.

SICHERHEITSDATEN

VOC-Gehalt:	max. 550 g/l
VOC-Gehalt Fertigmischung:	max. 550 g/l
VOC-Kategorie:	IIA/f
VOC-Grenzwert:	700g/l
Bemerkungen für Sicherheit:	Consult Safety Data Sheet and Safety. Information printed on the can.

LAGERFÄHIGKEIT

Mindestens 5 Jahre ab Fertigungsdatum in der ungeöffneten Originalverpackung bei Lagerung in trockenen, gut belüfteten Räumen, nicht in direktem Sonnenlicht, bei Temperaturen zwischen 5 - 35°C.

Ausgabedatum: 15/05/2024

Verfügbare Farben und Packungsgrößen: Bitte beziehen Sie sich auf die jeweilige Produktseite auf www.rust-oleum.eu für eine Übersicht der aktuell verfügbaren Farben und Größen verpacken.

Haftungsausschluss: Die hierin enthaltenen Informationen wurden nach bestem Wissen wahrheitsgetreu und präzise und im guten Glauben zusammengestellt. Wir übernehmen aber keine Haftung. Wir gehen davon aus, dass sich der Anwender eigenverantwortlich über die Eignung unserer Produkte für seine individuelle Zweckbestimmung informiert hat. Rust-Oleum Europe übernimmt keinerlei Haftung für Folgeschäden oder mittelbare Schäden. Die Produkte müssen gelagert, gehandhabt und unter Bedingungen verwendet werden, die den Empfehlungen von Rust-Oleum Europe entsprechen, die in der neuesten Ausgabe des Produktdatenblatts angegeben sind. Der Anwender muss sicherstellen, dass er die neueste Ausgabe besitzt. Die neuesten Ausgaben des Produktdatenblatts können kostenlos auf www.rust-oleum.eu heruntergeladen oder bei unserer Kundendienstabteilung angefordert werden. Rust-Oleum Europe behält sich das Recht vor, die Eigenschaften seiner Produkte ohne vorherige Ankündigung zu ändern.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu