

TIMBEREX

WOOD FINISHING OIL



TIMBEREX® THIXO

Transparent thixotropic wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film forming
- Enhances the wood structure

TIMBEREX® THIXO

DESCRIPTION

Slight thixotropic solvent based wood stain based on special urethane modified linseed oil alkyd resins. TIMBEREX® Thixo is an easy to apply thixotropic stain with great protective and cosmetic qualities with a slightly thicker texture than other wood-stains. This allows for a thicker coating of the product to be applied for better long-term protection and makes it more convenient to use, especially for overhead work. Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance – micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

UTILISATION RECOMMANDÉE

Protective and decorative impregnation of interior and exterior woodwork. Remark: colourless TIMBEREX Thixo is only suitable for internal use.

SYSTÈME RECOMMANDÉ

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit or similar.

Old stripped paint: rub down up to the bare non-impregnated wood and remove all dust before application.

Maintenance: clean substrate with white spirit and apply 2 or 3 thin coats of TIMBEREX Thixo.

DONNÉES TECHNIQUES

Densité (g/cm ³):	0.86 - 0.89
Niveau de brillance:	["Semi-Mat"]
Extrait sec en poids:	37 - 40%
Extrait sec en volume:	30 - 33%

TEMPS DE SÉCHAGE À 20°C/HR 50%

Au toucher:	3 hours
Manipulable:	3 hours
Recouvrable:	24 hours

EPAISSEUR DE FILM HUMIDE RECOMMANDÉE

100 micron (cons.: 10 m²/l)

EPAISSEUR DE FILM SEC RECOMMANDÉE

32 micron (cons.: 10 m²/l)

CONSOMMATION THÉORIQUE

10 m²/l

CONSOMMATION PRATIQUE

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÉCAUTIONS D'UTILISATION

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

CONDITIONS D'APPLICATION

Apply in a dry and well-ventilated area.

APPLICATION & DILUTION: BROSSE

By preference, apply undiluted.

APPLICATION & DILUTION: ROULEAU

By preference, apply undiluted.

APPLICATION & DILUTION: PISTOLET AIRLESS

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars

APPLICATION & DILUTION: PISTOLET PNEUMATIQUE

By preference, apply undiluted.

NETTOYAGE DU MATERIEL / ECLABOUSSURES

White spirit or similar

REMARQUES

Incorrect use of TIMBEREX Thixo means that it can still be fully or partly removed with White Spirit within the first few days after application.

DONNÉES DE SÉCURITÉ

Teneur en COV:	max. 550 g/l
COV prêt à l'emploi:	max. 550 g/l
Catégorie COV:	IIA/f
Limite COV:	700g/l
Remarques pour la sécurité:	Consult Safety Data Sheet and Safety. Information printed on the can.

DURÉE DE VIE

5 ans minimum à partir de la date de production (indiquée sur bidon) pour les bidons non ouverts, stockés au sec dans des locaux bien ventilés, à l'abri du rayonnement solaire, et à des températures comprises entre 5 et 35°C.

Date d'émission: 15/05/2024

Couleurs et conditionnements disponibles: Reportez-vous à la page produit concernée sur www.rust-oleum.eu pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

Notion de responsabilité: Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur www.rust-oleum.eu ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu