

TIMBEREX

WOOD FINISHING OIL



TIMBEREX® THIXO

Transparent thixotropic wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film forming
- Enhances the wood structure

TIMBEREX® THIXO

OMSCHRIJVING

Slight thixotropic solvent based wood stain based on special urethane modified linseed oil alkyd resins. TIMBEREX® Thixo is an easy to apply thixotropic stain with great protective and cosmetic qualities with a slightly thicker texture than other wood-stains. This allows for a thicker coating of the product to be applied for better long-term protection and makes it more convenient to use, especially for overhead work. Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance – micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

AANBEVOLEN GEBRUIK

Protective and decorative impregnation of interior and exterior woodwork. Remark: colourless TIMBEREX Thixo is only suitable for internal use.

AANBEVOLEN SYSTEEM

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit or similar.

Old stripped paint: rub down up to the bare non-impregnated wood and remove all dust before application.

Maintenance: clean substrate with white spirit and apply 2 or 3 thin coats of TIMBEREX Thixo.

TECHNISCHE GEGEVENS

Dichtheid (g/cm ³):	0.86 - 0.89
Glansgraad:	["Semi-Mat"]
Vaste stof gehalte in gewicht:	37 - 40%
Vaste stof gehalte in volume:	30 - 33%

DROOGTIJDEN BIJ 20° C/RV 50%

Kleefvrij:	3 hours
Hanteerbaar:	3 hours
Overschilderbaar:	24 hours

AANBEVOLEN NATTE LAAGDIKTE

100 micron (cons.: 10 m²/l)

AANBEVOLEN DROGE LAAGDIKTE

32 micron (cons.: 10 m²/l)

THEORETISCH VERBRUIK

10 m²/l

PRAKTISCH VERBRUIK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

INSTRUCTIES VOOR GEBRUIK

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATIEOMSTANDIGHEDEN

Apply in a dry and well-ventilated area.

VERDUNNING & APPLICATIE: KWAST

By preference, apply undiluted.

VERDUNNING & APPLICATIE: ROLLER

By preference, apply undiluted.

VERDUNNING & APPLICATIE: AIRLESS SPUIT

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars

VERDUNNING & APPLICATIE: LUCHTSPIJT

By preference, apply undiluted.

REINIGEN VAN APPARATUUR / SPATTEN

White spirit or similar

OPMERKINGEN

Incorrect use of TIMBEREX Thixo means that it can still be fully or partly removed with White Spirit within the first few days after application.

VEILIGHEIDSGEGEVENS

VOC gehalte:	max. 550 g/l
VOC readymix:	max. 550 g/l
VOC categorie:	IIA/f
VOC limiet:	700g/l
Opmerkingen mbt veiligheid:	Consult Safety Data Sheet and Safety. Information printed on the can.

HOUDBAARHEID

Minimaal 5 jaar vanaf productiedatum in ongeopende, originele verpakking, indien opgeslagen in droge, goed geventileerde ruimten, niet in de volle zon, bij temperaturen tussen 5 en 35°C.

Uitgiftedatum: 15/05/2024

Beschikbare kleuren en verpakkingsformaten: Raadpleeg de betreffende productpagina op www.rust-oleum.eu voor een overzicht van de actueel beschikbare kleuren en verpakkingsgrootten.

Disclaimer: De informatie in dit document is naar ons beste weten juist en wordt te goeder trouw, maar zonder garantie gegeven. De gebruiker wordt geacht onafhankelijk de geschiktheid van onze producten voor zijn/haar eigen specifieke toepassing te testen. In geen geval is Rust-Oleum Europe aansprakelijk voor directe of indirecte schade. Producten dienen te worden opgeslagen, behandeld en aangebracht volgens de aanbevelingen van Rust-Oleum Europe op het productinformatieblad (technische fiche). Het is de verantwoordelijkheid van de gebruiker om altijd de laatste versie van het productinformatieblad (technische fiche) te raadplegen en te respecteren. Deze bladen zijn gratis te downloaden van de website www.rust-oleum.eu of op aanvraag bij de afdeling Customer Service (Verkoop binnendienst). Rust-Oleum Europe houdt zich het recht voor om de eigenschappen van haar producten te wijzigen zonder voorafgaande kennisgeving.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu