

# TIMBEREX

WOOD FINISHING OIL



## TIMBEREX® THIXO

### Transparent thixotropic wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film forming
- Enhances the wood structure

# TIMBEREX® THIXO

## BESKRIVELSE

Slight thixotropic solvent based wood stain based on special urethane modified linseed oil alkyd resins. TIMBEREX® Thixo is an easy to apply thixotropic stain with great protective and cosmetic qualities with a slightly thicker texture than other wood-stains. This allows for a thicker coating of the product to be applied for better long-term protection and makes it more convenient to use, especially for overhead work. Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance – micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

## ANBEFALT BRUK

Protective and decorative impregnation of interior and exterior woodwork. Remark: colourless TIMBEREX Thixo is only suitable for internal use.

## ANBEFALT SYSTEM

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit or similar.

Old stripped paint: rub down up to the bare non-impregnated wood and remove all dust before application.

Maintenance: clean substrate with white spirit and apply 2 or 3 thin coats of TIMBEREX Thixo.

## TEKNISKE DATA

Tetthet:	0.86 - 0.89
Glansgrad:	semi_mat
Tørrstoffinnhold i vekt:	37 - 40%
Tørrstoffinnhold i volum:	30 - 33%

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støtørr:	3 hours
Håndterbar:	3 hours
Overmalbar:	24 hours

## ANBEFALT VÅTFILMTYKKELSE

100 micron (cons.: 10 m<sup>2</sup>/l)

## ANBEFALT TØRRFILMTYKKELSE

32 micron (cons.: 10 m<sup>2</sup>/l)

## TEORETISK FORBRUK

10 m<sup>2</sup>/l

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PÅFØRINGSBETINGELSER

Apply in a dry and well-ventilated area.

## PÅFØRING & FORTYNNING: PENSEL

By preference, apply undiluted.

## PÅFØRING & FORTYNNING: RULLE

By preference, apply undiluted.

## PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

By preference, apply undiluted.

## RENGJØRING AV UTSTYR/SPILL

White spirit or similar

## MERKNADER

Incorrect use of TIMBEREX Thixo means that it can still be fully or partly removed with White Spirit within the first few days after application.

## SIKKERHETSDATA

VOC nivå:	max. 550 g/l
VOC ferdigblandet:	max. 550 g/l
VOC kategori:	IIA/f
VOC grense:	700g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety. Information printed on the can.

## HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 24/03/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu