

TIMBEREX

WOOD FINISHING OIL



TIMBEREX® WAX OIL CLEAR

Quick drying oil containing Carnauba wax

- Suitable for all common wood types intended for both commercial and domestic situations
- Fast curing: application, wet- and dry-buffing on the same day
- Good coverage per litre
- Cures to a deep satin finish
- Easy to apply without any special tools

TIMBEREX® WAX OIL CLEAR

DESCRIPTION

Quick drying oil containing high-grade Carnauba wax, which greatly enhances colours and grain and allows wood to age naturally into rich varying tones. EN 71-3 certified (Toy Safe).

ODPORÚČANÉ POUŽITIE

Suitable for all common wood types intended for both commercial and domestic situations.

DRY TIMES BY 20° C/RH 50%

Suchý na opätovné natieranie: 20 - 45 minutes

Úplne vytvrdnuté: 7 days

TEORETICKÁ SPOTREBA

15 - 20 m² per litre (Priming)

> 50 m² per litre (Maintenance)

PRAKTICKÁ VÝDATNOSŤ

Can vary depending on wood-specie and preparation.

PRÍPRAVA POVRCHU

Punch down any nail heads, fill any small holes or imperfections with proprietary coloured timber filler (plastic wood) and leave to cure. The wood should not have excessive gaps through which the product could seep and affect the bond of any adhesive layer or rooms below. Floors should be free from any barrier to penetration. Sand at least twice starting with coarse sandpaper, and use 100 grade maximum sandpaper for the final preparatory sanding. Clean the surface by vacuuming and damp wipe the entire floor and allow to dry.

NÁVOD NA POUŽITIE

Due to the fast drying nature of the product, application can be completed in one day. It is advisable to test a small area first. Stir the product thoroughly before and during use to ensure consistent dispersion of the carnauba wax.

1. Apply the first coat of TIMBEREX® Wax-Oil using a brush, pad or roller. Accidental splashes on surrounding surfaces must be removed at once.
2. Apply a second coat after 20 - 45 minutes. Apply coats until the wood will not absorb any more oil. The oil must not dry between coats.
3. After another 20 - 45 minutes, thoroughly buff the wet surface using a buffer and medium grade nylon pad at approximately 150 rpm. Can be done manually as well.
4. Remove ALL unabsorbed TIMBEREX® Wax-Oil immediately with cloths, leaving a matt finish at this stage. Place all oil-impregnated cloths etc. into a bucket filled with water. See 'SAFETY' for further information.
5. When the surface has dried after 6-10 hours, it is important to thoroughly buff with a medium grade nylon pad to close the surface, provide a satin sheen and to remove any minor 'bleed-back'.

PODMIENKY APLIKÁCIE

The product should be stored at 20°C - 30°C for 8 hours prior to use.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Mild solvent, like white spirit etc.

POZNÁMKY

EQUIPMENT: Drum sander, sandpaper including 120 grade for final sanding, buffing machine (150-300 rpm), very stiff brush or squeegee, Red grade (optional) nylon buffing pads, strong buffing cloths and water bucket.

MAINTENANCE AND CLEANING: Floors which have been oiled for the first time should be treated with TIMBEREX® Wax-Oil after 6-12 months and thereafter once a year or when needed. Avoid alkaline soaps. Use TIMBEREX® Bio-C Cleaner for regular cleaning.

CURING The surface will normally be sufficiently dry to walk on after 24 hours. Dry vacuum only during the first 7 days and remove liquid spillages immediately. The surface will gradually increase in water resistance. Any initial light water marking is easily removed by soft nylon pad in conjunction with TIMBEREX® Wax-Oil.

SAFETY DATA

VOC readymix:

8g/L

Poznámky k bezpečnosti:

When sanding and sealing floors protective clothing should be worn including a face mask for dust filtration.

All product labels provide general safety information. Material safety data sheets are available on www.timberex.com. Food products must be removed from the area during application and cure.

Applicators, cloths etc impregnated with the product should be put in a bucket of water and placed outside the building to avoid the possibility of spontaneous combustion. The contents should be disposed of according to local regulations.

SKLADOVATELNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 24/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu